Faraday Discussions 162

Accepted Manuscript



RSCPublishing

This is an *Accepted Manuscript*, which has been through the RSC Publishing peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, which is prior to technical editing, formatting and proof reading. This free service from RSC Publishing allows authors to make their results available to the community, in citable form, before publication of the edited article. This *Accepted Manuscript* will be replaced by the edited and formatted *Advance Article* as soon as this is available.

To cite this manuscript please use its permanent Digital Object Identifier (DOI®), which is identical for all formats of publication.

More information about *Accepted Manuscripts* can be found in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics contained in the manuscript submitted by the author(s) which may alter content, and that the standard **Terms & Conditions** and the **ethical guidelines** that apply to the journal are still applicable. In no event shall the RSC be held responsible for any errors or omissions in these *Accepted Manuscript* manuscripts or any consequences arising from the use of any information contained in them.

RSCPublishing



Charge competition with oxygen molecules determines the growth of gold particles on doped CaO films

Yi Cui,¹ Kai Huang,¹ Niklas Nilius,^{1,2,} * Hans-Joachim Freund¹

¹ Fritz-Haber-Institut der Max-Planck-Gesellschaft, Faradayweg 4-6, 14195 Berlin, Germany

² Carl von Ossietzky Universität Oldenburg, Institut für Physik, D-26111 Oldenburg, Germany

The influence of gas-phase oxygen on the growth of Au nanoparticles on Mo-doped CaO films has been investigated by means of low temperature scanning tunnelling microscopy and X-ray photoelectron spectroscopy. Whereas at ideal vacuum conditions, only 2D Au islands develop on the oxide surface, the fraction of 3D deposits increases with increasing O_2 pressure until they become the dominant species in 10^{-6} mbar oxygen. The morphology crossover arises from changes in the interfacial electron flow between Mo donors in the CaO lattice and different ad-species on the oxide surface. In the absence of O_2 molecules, the donor electrons are predominately transferred to the Au ad-atoms, which consequently experience enhanced binding to the oxide surface and agglomerate into 2D islands. In an oxygen atmosphere, on the other hand, a substantial fraction of the excess electrons is trapped by adsorbed O_2 molecules, while the Au atoms remain neutral and assemble into tall 3D particles that are typical for non-doped oxides. Our experiments demonstrate how the competition for charge between different adsorbates governs the physical and chemical properties of doped oxides, so widely used in heterogeneous catalysis.

^{*} Corresponding author: nilius@fhi-berlin.mpg.de

The ability of supported metal particles to promote certain catalytic reactions depends on their elemental composition and the electronic and chemical interplay with the oxide support. Also the particle shape has proven to be of relevance, as certain reactions require the availability of specific active sites on the catalyst surface. A prominent example is the $CO \rightarrow CO_2$ conversion on supported metal catalysts, where the metal deposits are responsible for capturing the CO molecules, while the oxide stabilizes and activates the O₂ species. The actual reaction is then suggested to take place at the metal-oxide perimeter, explaining why particles with 2D or raft-like shapes are particularly suited to catalyze this reaction.^{1,2,3,4}

The geometry of metal particles on oxide supports has been investigated down to the atomic scale by using a variety of microscopic and spectroscopic techniques.^{5,6,7,8} The metal-oxide interface, i.e. the atomic registry and interfacial bond length, has thereby received special attention, as it governs the morphology of the growing aggregates.^{9,10} A careful shape characterization is also required in order to rationalize the particles electronic properties that, to a certain extent, reflect the symmetry of the confining potential and hence the position of the metal ion cores.¹¹ Whereas particle shapes could be analyzed only before and after a chemical reaction in the past,^{6,7,12} in-situ studies employing synchrotron-based EXAFS and environmental TEM now provide evidence for changes in coordination numbers and particle shapes directly during a catalytic process.^{13,14,15,16,17} In fact, the particles undergo substantial structural modifications at elevated pressure and temperature conditions, being explained with the different thermodynamic stability of bare and adsorbate-covered surfaces and the temporary formation of oxide and hydrate phases at reaction conditions.^{18,19}

In this paper, we demonstrate how the presence of a gas phase influences the growth behaviour of supported metal particles and how this effect depends on the state of doping of the oxide beneath. The phenomenon described here is therefore different from a pure environmental effect on existing particles, and sheds light on the interplay between adsorbates and dopants inside the oxide matrix on the growth process of metals. The effect of gas-phase species on the morphology of metal surfaces and nanopartices has been addressed in several experimental and theoretical studies before.^{20,21,22,23} The regular Pt(557) surface, for example, was found to develop a high density of kinks and corners in high-pressure CO,²⁴ but exposes ultra-small Pt nanoclusters in an

Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A

Faraday Discussions

 O_2 environment.²⁵ Electron-micrographs of individual Pt particles, on the other hand, revealed the transformation of (111) and (100) facets into various high-index planes upon O_2 exposure at 670 K.^{26,27} Similarly, the (100) facets of Au nanoclusters were shown to reconstruct in a CO environment in order to maximize the Au-CO interaction.²⁸ The observed restructuring is driven by the enhanced binding of most adsorbates to open, corrugated surfaces that are, however, thermodynamically unfavourable at vacuum conditions due to their high surface free energy.

A second effect on the particle morphology, the presence of dopants in the oxide lattice, has moved into the focus of catalysis research only recently. In a combined scanning tunnelling microscopy (STM) / density functional theory (DFT) study, it was shown that small quantities of Mo embedded in a CaO matrix substantially alters the growth morphology of gold.²⁹ Whereas mainly 3D deposits developed on the pristine oxide due to the weak metal-oxide adhesion in that case, monolayer Au islands occurred after doping with Mo. The morphology crossover was explained with an electron transfer from the Mo donors into the ad-gold, activating efficient Au-CaO interaction channels.³⁰ The reverse effect was found upon inserting low-valence dopants, e.g. Li, into the CaO lattice. The Li ions generate acceptor-type hole-states in the oxide valence band, which effectively trap excess electrons and prevent their transfer into the ad-gold. The neutral gold follows a 3D growth behaviour, similar to the one on non-doped supports.³¹ In this paper, we demonstrate how a variable background of O₂ alters the charge-exchange between donors in the CaO lattice and adsorbed Au species. We show that gold grows into tall 3D deposits in the presence of oxygen and discuss possible implications of the underlying charge competition on the catalytic properties of doped metal-oxide systems.

EXPERIMENTAL

The studies were performed in an ultra-high vacuum (UHV) chamber equipped with a lowtemperature STM (T = 9.5 K) and an X-ray photoelectron spectrometer (ESCALAB 200). The CaO films were prepared by Ca deposition onto a Mo(001) surface in 5×10⁻⁷ mbar O₂ at room temperature, followed by an annealing step to 1000 K in UHV.³² The films contained a significant amount of Mo impurities, originating from atom diffusion out of the metal support into Ca substitutional sites of the CaO lattice. Due to a relatively large Mo diffusion barrier, the impurity concentration gradually diminished with film thickness from 25% directly at the interface to almost zero beyond the 20th monolayer (ML).³³ For 20-25 ML thick films used in the experiment, the mean Mo concentration in the near-surface region was estimated to be 2-3%. Practically dopant-free films, being referred to as pristine films in the following, could be produced by increasing the CaO thickness to around 50 ML. Both, the self-doped and pristine films displayed a sharp (1×1) square pattern in LEED, indicative for a fully relaxed, (001)-terminated rocksalt structure. XPS measurements confirmed the one-to-one stoichiometry of the CaO films and the presence of Mo dopants at low film thicknesses. The oxide surface consisted of atomically flat domains of up to 100 nm² size, separated by predominately [100] oriented line defects, as derived from the STM data.³² The dislocation network developed spontaneously in the oxide film in order to remove misfit-induced lattice strain with the metal substrate. The Au particles were prepared by depositing nominally 0.5 ML gold from a thermal evaporator using a deposition rate of 0.5 ML/min. In order to investigate the impact of oxygen on the Au growth, the samples have been exposed to different O₂ partial pressures at 300 K before, during or after gold exposure.

RESULTS

As discussed in earlier work,²⁹ Au growth on pristine and Mo-doped CaO films proceeds in almost opposite manner (Fig. 1a,b). While on pristine films, the Au particles adopt large heightto-diameter ratios indicative for a small metal-oxide adhesion, flat, monolayer islands develop in the presence of Mo-dopants. The drastic change in particle morphology becomes evident in shape histograms, being produced by analysing a few hundred Au deposits on differently prepared oxide films (Fig. 2). Interestingly, the growth behaviour was found to be sensitive not only to the presence of dopants, but also to the gas atmosphere in which metal deposition was carried out. In 5×10^{-8} mbar O₂, the Au growth starts diverging from the ideal 2D regime that is typical for doped films, and 3D deposits become visible in the STM (Fig. 1c and 2c). The alteration of the growth mode initially affects only particles around the oxide dislocation lines. However, with increasing O₂ partial pressure, 3D particles appear even away from the surface defects. In 5×10^{-7} mbar of oxygen, already half of the Au deposits adopt 3D geometries, while the remaining entities still retain a monolayer nature (Fig. 1d). Surprisingly, no intermediate particle shapes are detected, causing the particle shape distribution to become strongly bimodal

Faraday Discussions Accepted Manuscript

(Fig. 2d). At 5×10^{-6} mbar oxygen pressure, 3D shapes entirely dominated the Au particle ensemble, while 2D islands have vanished from the histogram. This growth situation does not change anymore at higher O₂ partial pressures, only that the CaO surface starts degrading at such conditions (Fig. 1f). We relate the observed roughening effect to two factors. First, our O_2 gas source might be contaminated with traces of water that interacts with the hydrophilic CaO surface and gradually transforms it into a disordered calcium-hydroxide phase. Second, the excess oxygen might promote Mo segregation from the interior of the CaO film to its surface, where it aggregates into a rough Mo-oxide overlayer. Such a segregation process is thermodynamically feasible due to a substantial energy gain when changing the oxidation state of Mo ions from +2 in an ideal rocksalt environment to +6 in saturated MoO₃ surface units.³³ As a consequence of the reduced surface quality, also the density of Au particles increases at high O₂ partial pressures, as new nucleation sites becomes available for the incoming Au atoms (Fig. 2f). In a second set of experiments, we have analysed the influence of pre-dosed oxygen on the growth morphology of gold. For this purpose, the CaO films were exposed to 20 L O_2 prior to Au deposition, where they produced distinct oval depressions of 0.5 Å depth in the STM images (Fig. 3a). Following earlier DFT calculations, 34,35 we assign those entities to O₂ molecules that lie flat on the surface and therefore appear slightly elongated. This interpretation is supported by manipulation experiments, in which selected O₂ molecules were split into their atomic constituents by applying a 3.0 V pulse to the STM tip,³⁶ as shown in Ref. [37]. Also pre-dosed oxygen was found to alter the Au growth morphology, although the actual deposition step was performed in UHV. The particle ensembles prepared on a Mo-doped, O_2 pre-covered CaO have the same bimodal shape distribution as the ones produced in moderate O₂ background pressure (Fig. 3c). Apparently, surface-bound and gas-phase molecules play a similar role, i.e. they promote the development of 3D instead of 2D particles even on doped oxide films. Only the efficiency of the geometry crossover is reduced, a trend that is easily explained with the smaller availability of surface oxygen at pre-dosing conditions compared to continuous dosing.

Finally, we have explored the effect of post-oxidizing the Au particles. As discussed before, gold exposure in UHV produces 2D metal sheets on the Mo-doped CaO surface.²⁹ Exposing such an ensemble to 100 L O_2 does not affect the original 2D particle shape (Fig. 3d). In fact, the main difference between as-grown and post-oxidized Au islands is a characteristic rim in the latter

Faraday Discussions

Accepted Manuscript

aradav Discussions

case, being assigned to adsorbed molecules along the low-coordinated island perimeter.³⁸ On thick, non-doped CaO films, the Au growth morphology was found to be independent of oxygen, as the molecules only stabilize the 3D growth mode that is intrinsic to the pristine oxide.

Before discussing the effect of oxygen on the Au growth, we want to highlight another interesting phenomenon. Although 3D particles develop on both, non-doped CaO in vacuum and Mo-doped CaO in an O₂ environment, the resulting particle shapes are rather different. Vacuumgrown particles are mostly hemispherical and do not exhibit well-shaped basal planes or side facets (Fig. 1a). As we are still assured of their crystalline nature, we tentatively assign them to fcc-semispheres being densely covered by step edges. In contrast, particles grown in an oxygen environment have distinct geometries, as depicted in Fig.4. The most abundant particle type has a quasi-rectangular basal plane and two roof-like side facets extending along its main axis (Fig. 4b). The particle orientation always follows a [100] or [010] direction of the CaO(001) lattice, indicating an epitaxial relationship between gold the CaO surface. A second, frequently observed particle type has a truncated pyramidal shape with three large and three small side facets (Fig. 4c). Finally, particles with hexagonal or octahedral base planes and pyramidal appearance are found at oxygen-rich conditions (Fig. 4e). The latter two types have a random orientation with respect to the CaO lattice and are less abundant than the roof-like deposits. In general, the 3D deposits produced in an O₂ environment feature higher crystallinity than the vacuum-grown speices, suggesting that the surface-oxygen increases the mobility of the Au atoms and hence facilitates their aggregation process.¹²

DISCUSSION

According to the main experimental observations, we divide our discussion into two parts that are (i) the transition from 2D to 3D deposits upon gold deposition at increasing O_2 partial pressures and (ii) the improved crystallinity of particles grown in oxygen excess.

The fundamental reason for the development of 2D Au islands on Mo-doped CaO films is an electron transfer from the Mo donors into the Au ad-species.^{29,39} The process is energetically favourable as the filled *Mo 4d* states in the CaO band gap are higher in energy than the *Au 6s* affinity levels. Thus produced Au^- species experience effective interaction schemes with the CaO support, namely Coulomb attraction to the oxide cations and polaronic stabilization of the

Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A

Au⁻ on the ionic surface,³⁰ which in turn promote a 2D growth regime on the doped oxide film (see Fig. 1b). The impact of oxygen on the Mo-Au charge exchange now provides a plausible explanation for the modified Au growth behaviour at non-vacuum conditions. Similar to gold, the O₂ molecules are electron acceptors and able to trap Mo excess electrons in their low-lying antibonding orbitals. Taking the electron affinity of the gas-phase species as reference (EA = 0.5eV),⁴⁰ the lowest acceptor level of the molecule lies below the highest occupied Mo 4d gap state, which renders formation of surface O_2^- species feasible. Co-deposition of oxygen and gold leads therefore to a situation in which both adsorbates compete for charges from the Mo impurities. For the experimental Au deposition rate of 0.5 ML/min and different O₂ partial pressures, the following interplay occurs between the ad-species on the CaO surface. At the lowest O2 pressure (10⁻⁸ mbar), the number of both, Au atoms and O₂ molecules increases by roughly 1×10^{13} cm⁻² per second, assuming a sticking of one. However, as gold is the much stronger electron acceptor $(EA = 2.3 \text{ eV})^{40}$ most extra charges get trapped by the Au atoms and their growth behaviour changes only moderately (Fig. 1c). Deviations from the 2D growth mode are only observed around the CaO dislocation lines, where empty defect states in the band gap emerge as third opponent in the charge competition.⁴¹ At 10⁻⁷ mbar O₂, every incoming Au atom already faces 10 O₂ molecules on the surface. Moreover, the charge reservoir established by near-surface Mo donors quickly depletes due to the high number of oxygen acceptors on the surface. However, as not every O₂ molecule immediately sticks and takes an electron, a dynamical situation arises in which the Au atoms are still able to attract a substantial charge fraction from the Mo dopants. This new balance gives rise to a bimodal shape distribution in which 2D and 3D deposits coexist on the CaO surface (Fig. 2c). At 10^{-6} mbar O₂, finally, the ratio between O₂ and Au species approaches 100:1 and acquisition of relevant charge quantities becomes difficult for the gold. Consequently, most Au atoms remain neutral and grow into tall 3D deposits right from the beginning. The resulting small interface area with the CaO support hampers the electron transfer also in a later stage, further stabilizing the 3D growth regime of Au in this stage (Fig. 1e).

To support the scenario of charge competition, we give circumstantial evidence for a negative charging of Au and O_2 species on the CaO surface. The charge donation from the Mo impurities can be derived indirectly from changes in the CaO electronic structure. In STM conductance spectra, an up-shift of the oxide valence and conduction band by around 1.0 V is revealed upon

Faraday Discussions Accepted Manuscript

oxygen exposure (Fig. 3b), an effect that was also observed after Au deposition onto the doped CaO films.³³ XP-spectra show a similar trend and both, the *O1s* and *Ca2p* core levels lower their binding energy upon dosing the electron-accepting species (0.3 and 0.2 eV for Au and O₂ exposure, respectively, Fig.5). We relate this shift to an upward bending of the oxide bands, induced by the enhanced *e-e* repulsion between adsorbates and oxide electronic states in response to the electron transfer from the Mo donors.³¹ The magnitude of the effect is smaller in XPS than STM due to the extreme surface sensitivity of the latter technique. Note that the presence of neutral or positively-charged adsorbates would lead to a constant or down-shifted state-density, in disagreement with the experimental data. The corresponding shift of the Mo *3d* core levels could not be resolved in our XP data because of the low dopant concentration and the poor signal-to-noise ratio. This information needs to be obtained with a synchrotron-based experiment in future.

A charge transfer into oxygen and mediated by this, a strengthening of the O₂-CaO interaction, is also in line with the observed thermal stability of O₂ at room temperature and the easiness to image the molecules in the STM even on thick oxide films. On non-doped wide-gap insulators, such as MgO and Al₂O₃, molecular O₂ typically desorbs well below 300 K and is hard to detect in STM even at cryogenic temperature.^{42,43} Moreover, recent electron-paramagnetic-resonance studies indicated the formation of O₂⁻ species on ultrathin MgO/Ag films, with the only difference that the extra electrons originated from the metal support below the film and not from donors inside the oxide as in our case.⁴⁴ The maximum density of O₂⁻ species was determined to be 10^{13} cm⁻², a value that is likely higher on the more basic CaO surface.⁴⁴ We finally note that surface-bound oxygen may not only alter the charge-transfer into the gold, but also reduce the Au-CaO adhesion directly, e.g. by forming a chemisorbed oxygen layer just below the growing ad-islands.^{19,45} The reduced interface interaction in this case would shift the Au equilibrium shape towards 3D, reflecting Wulff's principle that a smaller adhesion leads to larger particle heights.^{6,46} We anticipate however that this effect is less relevant for our experimental results than the charge competition between the two electron-accepting adsorbates.

In the last paragraph, we discuss the improved crystallinity of Au deposits grown at O_2 -rich conditions and try to rationalize the observe particle geometries. The most abundant particle type

Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A

is a roof-like crystallite oriented along a CaO[100] direction (Fig. 4b). Its elongated shape indicates a strong unidirectional growth and a pseudomorphic relationship with the CaO(001)lattice beneath. As a hexagonal Au(111) interface, being the thermodynamically favoured termination of fcc-gold, is incompatible with an epitaxial growth on the square oxide lattice, we suggest that gold crystallizes in an hcp lattice and develops (1120) interface planes. This growth motive has recently been identified for Ni and Mg deposits grown on the iso-structural MgO(001) surface.^{10,47} Due to the two-fold symmetry of the hcp (1120) plane, a dense array of metal-oxygen bonds is formed across the interface that substantially contributes to the metaloxide adhesion. A similar interface geometry can be realized for hcp Au ($11\overline{2}0$) planes on the slightly larger CaO(001) lattice. The required distortion of the Au lattice amounts to 2% and -4%along the two orthogonal CaO[100] directions, respectively, values that are in reach for metal nanoclusters with their high structural flexibility (Fig. 4d). A $(11\overline{20})$ interface would also explain the unidirectional growth of gold, as the particles primarily expand along the low-strain direction on the CaO support. Even the side-facets of the roof-shaped Au deposits can be assigned in this case. The most plausible candidates are the hcp (0001) planes, which are tilted by 45° against the surface and characterized by particularly low surface free energies due to their closed-packed nature. We finally note that DFT calculations found similar total energies for Au_{40} clusters in either hcp or fcc configuration on the CaO(001), suggesting that both growth modes are energetically accesible.47

Apart from the roof-shaped crystallites, none of the other particle types develop an epitaxial relationship with the square CaO(001) lattice (Fig. 4c,e). Evidently, those deposits have other means to interact with the oxide support and are not forced to grow in registry with the oxide lattice. Icosdahedral and pyramidal particle shapes have been observed for various metals (Au, Ag, Pd and Cu) on different oxide supports before, e.g. on hexagonal Al₂O₃(0001),⁵ square MgO(001)¹⁰ and SrTiO₃(001),^{48,49} especially at high deposition temperature. This universality suggests that such geometries are determined by the low formation energy of (111) facets of fcc metals and follow the classical Wulff construction principle for metal crystallites on weakly interacting supports.^{46,50} The abundance of epitaxial hcp versus symmetry-mismatched fcc deposits is again connected to the role of oxygen in the particle growth. At O₂-rich conditions $(1\times10^{-6} \text{ mbar O}_2)$, the ad-gold is unable to acquire charges from the Mo donors and remains

neutral. Interfacial Au- O_{CaO} bonds are thus a crucial means to anchor the particles on the CaO surface, a fact that promotes the formation of epitaxial hcp(1120) interface planes. With an enhanced electron flow to the gold at lower O_2 pressures, charge-mediated interaction schemes become available. As a result, the particles gain structural flexibility and adopt growth shapes that are energetically more favorable than the hcp configuration. In the limit of zero oxygen, the Mo excess charges entirely govern the growth on the CaO surface and the gold spreads into large, monolayer islands.²⁹

We note that other oxygen-induced effects may contribute to the particle shapes observed in our experiment. Oxygen is a well-known surfactant⁵¹ and increases the mobility of Au adatoms by forming intermediate metal-oxygen units. A higher diffusivity of the incoming species naturally improves the crystallinity of the ad-particles. In addition, O₂ adsorption may selectively stabilize certain Au facets,⁴⁵ modifying the particle equilibrium shape as compared to UHV conditions. ^{25,26} Given the weakness of the oxygen-Au bond,⁴⁰ we believe however that direct adsorption of O₂ species is only of minor importance for the growth morphology of the Au particles.

SUMMARY

Using a combined STM and XPS approach, we have demonstrated that the equilibrium shape of nanoparticles on doped CaO films results from a competition for electrons between Au atoms and oxygen species. At vacuum conditions, excess electrons provided by Mo ions in the oxide lattice are transferred to incoming Au atoms, which subsequently agglomerate into flat 2D islands in order to maximize the metal-oxide adhesion. Simultaneous oxygen supply from the gas phase interrupts this electron flow, as the surface O_2 species are able to trap extra electrons as well. Once the majority of electrons get stabilized by O_2 molecules, the Au growth changes from a 2D to a 3D mode, the latter being characteristic for non-doped oxides. The oxygen-induced morphology crossover is irreversible and the Au particles retain a 3D shape even after the oxygen has been removed from the system.

Our paper highlights the complexity of charge-transfer processes between dielectric supports, admetals and molecules, a combination of matter that typically occurs in heterogeneous catalysis.

Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A

The direction of the charge flow is given by the actual potential situation at the catalyst surface, the relative energies of competing donor and acceptor levels and finally the electro-negativity of the involved molecules. The efficiency of the charge transfer therefore depends not only on intrinsic catalyst properties but also on the composition of the surrounding gas phase. The highly dynamic nature of charge transfer processes calls for an exploration of catalytically-relevant systems directly at operation conditions. Our findings also disclose a possibility to alter the growth mode of metals simply by changing the gas atmosphere during deposition, opening a new pathway to optimize structure and morphology of supported metal catalysts.

Acknowledgments: The authors are grateful for financial support from the DFG within the Cluster of Excellence 'Unicat'. Y.C. thanks the Humboldt Foundation for a fellowship.



Fig. 1: STM topographic images of 0.5 ML gold deposited on (**a**) 50 ML CaO without dopants in the surface region and on 25 ML thick, self-doped CaO films (**b**) in UHV and (**c-f**) in O₂ pressures increasing from (**c**) 5×10^{-8} mbar, (**d**) 5×10^{-7} mbar, (**e**) 5×10^{-6} mbar to (**f**) 2×10^{-5} mbar. All images are 50×50 nm² in size and have been obtained at 4.0 V sample bias. Note that 2D Au islands are imaged as depressions on the CaO due to their low conductivity.³³ In (c,d), the islands are marked by dashed lines.



Fig. 2: Histograms of Au-particle shapes for growth conditions identical to the ones shown in Fig.1: (a) non-doped CaO in UHV, Mo-doped CaO in (b) UHV, (c) 5×10^{-8} mbar, (d) 5×10^{-7} mbar and (e) 5×10^{-6} mbar of oxygen. The occurrence of negative aspect ratios in the histograms relates to the negative contrast of monolayer Au islands in the respective STM images. Note the bimodal shape distributions in panels (c) and (d), reflecting the coexistence of 2D and 3D particles. (f) Evolution of the number density of 2D and 3D deposits as a function of the O₂ pressure during deposition.



Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A

Fig. 3: (a) STM topographic image of a Mo-doped CaO film after exposure to 20 L of oxygen (25×25). (b) Conductance spectra showing the onset of valence and conduction band on clean and O₂-covered CaO films. (c) 0.5 ML Au deposited onto a Modoped CaO film pre-covered with 400 L O₂ and (d) 0.5 ML Au post-oxidized with 100 L O₂ (40×40 nm²). The 2D islands are marked with dashed lines. The inset in (d) shows a selected Au monolayer island with an oxidized rim $(10 \times 10 \text{ nm}^2)$.

Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A



Fig. 4: (a) Pseudo-3D representation of crystalline Au particles grown on a Mo-doped CaO film in 5×10^{-6} mbar O₂(50×50 nm²). Enlarged images of four particles with (b) roof-like, (c) truncated pyramidal (8×8 nm²) and (e) hexagonal and octahedral shapes (8×12 nm²). The particle edges are retraced with dashed lines. (d) Ball model showing the hcp-Au (1120)/CaO(001) interface that gets pseudomorphic upon slight distortion of the Au bulk lattice. The A and B planes of the hcp lattice are indicated with arrows.



Fig 5. XP spectra of Ca 2p and O 1s peaks of a Modoped CaO film before and after (a,b) Au deposition and (c,d) O₂ exposure. In both cases, the oxide states experience a shift to lower binding energies as a response to the charge transfer into the adsobates.

- ¹ L. M. Molina and B. Hammer, Appl. Catal. A: Gen., 2005, 291, 21-31.
- ² M. Chen and D. W. Goodman, Accounts. Chem. Res., 2006, **39**, 739-746.
- ³ I. X. Green, W. Tang, M. Neurock and J. T. Yates, *Science*, 2011, **333**, 736-739.
- ⁴ A. A. Herzing, C. J. Kiely, A. F. Carley, P. Landon and G. J. Hutchings, *Science*, 2008, **321**, 1331-1335.
- ⁵ K. H. Hansen, T. Worren, S. Stempel, E. Lægsgaard, M. Bäumer, H. J. Freund, F. Besenbacher and I. Stensgaard, *Phys. Rev. Lett.*, 1999, 83, 4120-4123.
- ⁶ M. Bäumer and H.-J. Freund, Prog. Surf. Sci., 1999, **61**, 127-198.
- ⁷ C. R. Henry, *Prog. Surf. Sci.*, 2005, **80**, 92-116.
- ⁸ G. J. Hutchings, Chem. Commun., 2008, 1148-1164.
- ⁹ G. Pacchioni and N. Rosch, J. Chem. Phys., 1996, 104, 7329-7337.
- ¹⁰ S. Benedetti, P. Myrach, A. di Bona, S. Valeri, N. Nilius and H.-J. Freund, *Phys. Rev. B*, 2011, 83, 125423.
- ¹¹ X. Lin, N. Nilius, H. J. Freund, M. Walter, P. Frondelius, K. Honkala and H. Häkkinen, *Phys. Rev. Lett.*, 2009, **102**, 206801-206804.
- ¹² D. Starr, S. Shaikhutdinov and H.-J. Freund, *Top. Catal.*, 2005, **36**, 33-41.
- ¹³ J.-D. Grunwaldt and B. Clausen, *Top. Catal.*, 2002, **18**, 37-43.
- ¹⁴ P. L. Hansen, J. B. Wagner, S. Helveg, J. R. Rostrup-Nielsen, B. S. Clausen, H. Topsøe, *Science*, 2002, 295, 2053-2055.
- ¹⁵ G. Jacobs, J. A. Chaney, P. M. Patterson, T. K. Das and B. H. Davis, *Appl. Catal. A: Gen.*, 2004, 264, 203-212.
- ¹⁶ S. Mostafa, F. Behafarid, J. R. Croy, L. K. Ono, L. Li, J. C. Yang, A. I. Frenkel and B. R. Cuenya, J. Am. Chem. Soc., 2010, **132**, 15714-15719.
- ¹⁷ M. W. Small, S. I. Sanchez, N. S. Marinkovic, A. I. Frenkel and R. G. Nuzzo, *ACS Nano*, 2012, 6, 5583-5595.
- ¹⁸ M. D. Ackermann, T. M. Pedersen, B. L. M. Hendriksen, O. Robach, S. C. Bobaru, I. Popa, C. Quiros, H. Kim, B. Hammer, S. Ferrer and J. W. M. Frenken, *Phys. Rev. Lett.*, 2005, **95**, 255505-255508.
- ¹⁹ T. Schalow, M. Laurin, B. Brandt, S. Schauermann, S. Guimond, H. Kuhlenbeck, D. E. Starr, S. K. Shaikhutdinov, J. Libuda and H. J. Freund, *Angew. Chem. Int. Ed.*, 2005, 44, 7601-7605.
- ²⁰ S. Giorgio, M. Cabié and C. R. Henry, *Gold. Bull.*, 2008, **41**, 167-173.
- ²¹ B. J. McIntyre, M. Salmeron, G. A. Somorjai, J. Vac. Sci. Technol. 1993, **11**, 1964-1968.
- ²² G. A. Somorjai , G. Rupprechter, J. Phys. Chem. B 1999, 103, 1623-1638.
- ²³ K. P. McKenna and A. L. Shluger, J. Phys. Chem. C, 2007, **111**, 18848-18852.
- ²⁴ F. Tao, S. Dag, L.-W. Wang, Z. Liu, D. R. Butcher, H. Bluhm, M. Salmeron and G. A. Somorjai, *Science*, 2010, **327**, 850-853.
- ²⁵ Z. Zhu, F. Tao, F. Zheng, R. Chang, Y. Li, L. Heinke, Z. Liu, M. Salmeron and G. A. Somorjai, *Nano Lett.*, 2012, **12**, 1491-1497.
- ²⁶ M. Cabié, S. Giorgio, C. R. Henry, M. R. Axet, K. Philippot and B. Chaudret, J. Phys. Chem. C, 2010, 114, 2160-2163.

Published on 08 January 2013 on http://pubs.rsc.org | doi:10.1039/C3FD20130A

- ²⁷ G. Rupprechter and H.-J. Freund, *Top. Catal.*, 2000, **14**, 3-14.
- ²⁸ H. Yoshida, Y. Kuwauchi, J. R. Jinschek, K. Sun, S. Tanaka, M. Kohyama, S. Shimada, M. Haruta and S. Takeda, *Science*, 2012, **335**, 317-319.
- ²⁹ X. Shao, S. Prada, L. Giordano, G. Pacchioni, N. Nilius and H. J. Freund, *Angew. Chem. Int. Ed.*, 2011, 50, 11525-11527.
- ³⁰ G. Pacchioni, L. Giordano and M. Baistrocchi, *Phys. Rev. Lett.*, 2005, **94**, 226104-226107.
- ³¹ X. Shao, N. Nilius and H. J. Freund, J. Am. Chem. Soc., 2012, **134**, 2532-2534.
- ³² X. Shao, P. Myrach, N. Nilius and H. J. Freund, J. Phys. Chem. C, 2011, **115**, 8784-8789.
- ³³ X. Shao, N. Nilius, P. Myrach, H. J. Freund, U. Martinez, S. Prada, L. Giordano and G. Pacchioni, *Phys. Rev. B*, 2011, **83**, 245407-245411; X. Shao, N. Nilius and H. J. Freund, *Phys. Rev. B*, 2012, **85**, 115444-115451.
- ³⁴ N. U. Zhanpeisov, V. Staemmler and M. Baerns, J. Mol. Catal. A: chem., 1995, **101**, 51-60.
- ³⁵ L. Wang, Appl. Surf. Sci., 2011, 257, 5499-5502.
- ³⁶ B. C. Stipe, M. A. Rezaei, W. Ho, S. Gao, M. Persson and B. I. Lundqvist, *Phys. Rev. Lett.*, 1997, 78, 4410-4413.
- ³⁷ Y.Cui, X. Shao, K. Huang, N. Nilius, H-J. Freund, in preparation.
- ³⁸ P. Frondelius, H. Häkkinen and K. Honkala, Angew. Chem. Int. Ed., 2010, 49, 7913-7916.
- ³⁹ F. Stavale, X. Shao, N. Nilius, H. J. Freund, S. Prada, L. Giordano and G. Pacchioni, J. Am. Chem. Soc., 2012, **134**, 11380-11383.
- ⁴⁰ D. R Lide (Ed), CRC handbook of chemistry and physics, (Boca Raton, CRC Press, 2010).
- ⁴¹ H.-M. Benia, P. Myrach, A. Gonchar, T. Risse, N. Nilius and H.-J. Freund, *Phys. Rev. B*, 2010, **81**, 241415-241418.
- ⁴² R. M. Jaeger, J. Libuda, M. Bäumer, K. Homann, H. Kuhlenbeck and H. J. Freund, J. Electron Spectrosc., 1993, 64–65, 217-225.
- ⁴³ H.-J. Freund, Th. Klüner, R. Wichtendahl, S. Thiel, M. Adelt, W. Drachsel, M. Bäumer, H. Kuhlenbeck, T. Risse, K. Al-Shamery, M. Kampling, H. Hamann; 'Metal-Ligand Interactions in Chemistry, Physics and Biology', NATO ASI Ser., Vol. E, p. 91-128, (Kluwer, Academic Publ, 2000).
- ⁴⁴ A. Gonchar, T. Risse, H. J. Freund, L. Giordano, C. Di Valentin and G. Pacchioni, *Angew. Chem. Int. Ed.*, 2011, **50**, 2635-2638.
- ⁴⁵ J. M. Gottfried, K. J. Schmidt, S. L. M. Schroeder and K. Christmann, Surf. Sci., 2002, **511**, 65-82.
- ⁴⁶ G. Wulff, Z. Kryst. 1901, 34, 449-530.
- ⁴⁷ R. Ferrando, G. Rossi, F. Nita, G. Barcaro and A. Fortunelli, *ACS Nano*, 2008, **2**, 1849-1856.
- ⁴⁸ F. Silly and M. R. Castell, *Phys. Rev. Lett.*, 2006, **96**, 086104-086107.
- ⁴⁹ F. Silly and M. R. Castell, *Appl. Phys. Lett.*, 2005, **87**, 213107-213103.; F. Silly, A. C. Powell, M. G. Martin and M. R. Castell, *Phys. Rev. B*, 2005, **72**, 165403-165408.
- ⁵⁰ N. Cabrera, *Surf. Sci.*, 1964, **2**, 320-345.
- ⁵¹ H. Wolter, K. Meinel, C. Ammer, K. Wandelt and H. Neddermeyer, *Phys. Rev. B*, 1997, **56**, 15459-15470.

Faraday Discussions Accepted Manuscript

